

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|-------------------------------------|-------|-------------------|---------------|
| ASTM Data | | | |
| Melt Flow Index, MFI | 0.7 | g/10min | ASTM D 1238 |
| Temperature | 230 | °C | - |
| Load | 2.16 | kg | - |
| Mechanical properties | | | |
| ISO Data | | | |
| Yield stress | 25 | MPa | ISO 527 |
| Flexural modulus, 23°C | 1100 | MPa | ISO 178 |
| Izod notched impact strength, +23°C | 70 | kJ/m ² | ISO 180/1A |
| Other properties | | | |
| Density | 910 | kg/m ³ | ISO 1183 |

Characteristics

Processing

Pipe/Tube Extrusion, Profile Extrusion, Sheet Extrusion

Special Characteristics

U.V. stabilized or stable to weather

Features

Melt Strength, Copolymer, Impact Copolymer

Regional Availability

North America, Asia Pacific, South and Central America, Near East/Africa