

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	13	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Melt flow index, MFI	11	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	2000	MPa	ISO 527
Yield stress	36	MPa	ISO 527
Yield strain	9	%	ISO 527
Flexural modulus, 23°C	1900	MPa	ISO 178
Charpy impact strength, +23°C	80	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	3.5	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	55	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	115	°C	ISO 75-1/-2
Other properties			
Density	920	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Regional Availability

Europe

Features

Homopolymer