

**Hostacom PPU X9067HS 95T CORNSILK**

PP

LyondellBasell Industries

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>13.5</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Yield stress	<b>22</b>	MPa	ISO 527
Yield strain	<b>4</b>	%	ISO 527
Flexural modulus, 23°C	<b>1300</b>	MPa	ISO 178
Charpy notched impact strength, +23°C	<b>8</b>	kJ/m <sup>2</sup>	ISO 179/1eA

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>910</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding

**Applications**

Automotive

**Features**

Copolymer

**Regional Availability**

North America