

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	13.5	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	22	MPa	ISO 527
Yield strain	4	%	ISO 527
Flexural modulus, 23°C	1300	MPa	ISO 178
Charpy notched impact strength, +23°C	8	kJ/m ²	ISO 179/1eA
Other properties			
Density	910	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Applications

Automotive

Features

Copolymer

Regional Availability

North America