

Hostacom TRS 217N C12507

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	15	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	21	MPa	ISO 527
Flexural modulus, 23°C	1550	MPa	ISO 178
Charpy notched impact strength, +23°C	20	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	5	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Vicat softening temperature, A	142	°C	ISO 306
Other properties			
ISO Data			
Density	910	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Features

Non Blooming, Copolymer

Delivery form

Pellets

Regional Availability

Europe