

Hostalen PP H2250 36

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	0.3	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	36	MPa	ISO 527
Yield strain	12	%	ISO 527
Charpy notched impact strength, +23°C	26	kJ/m ²	ISO 179/1eA
Ball indentation hardness	66	MPa	ISO 2039-1

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	159	°C	ISO 11357-1/-3
Temp. of deflection under load, 0.45 MPa	98	°C	ISO 75-1/-2
Vicat softening temperature, A	157	°C	ISO 306
Vicat softening temperature, B	95	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ISO 1183

Characteristics**Processing**

Pipe/Tube Extrusion, Sheet Extrusion, Other Extrusion

Special Characteristics

Heat stabilized or stable to heat

Features

Homopolymer

Chemical Resistance

Oxidation Resistance

Certifications

Food contact, Food approval 1935/2004/EC, Food approval 10/2011, Food approval FDA 21 CFR

Regional Availability

Europe