

Hostalen PP XN125-P

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	0.4	g/10min	ISO 1133
Temperature	190	°C	-
Load	5	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	850	MPa	ISO 527
Yield stress	26	MPa	ISO 527
Yield strain	12	%	ISO 527

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	136	°C	ISO 11357-1/-3

Characteristics**Processing**

Pipe/Tube Extrusion, Sheet Extrusion, Other Extrusion

Delivery form

Natural Color

Features

Copolymer, Random Copolymer

Chemical Resistance

Oxidation Resistance

Certifications

Food contact, Food approval 1935/2004/EC, Food approval 10/2011, Food approval FDA 21 CFR

Regional Availability

Europe