

**HP522J**

PP

Rayomand Petroleum and Energy Commercial Co.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>3</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	<b>1370</b>	MPa	ISO 527
Yield stress	<b>33</b>	MPa	ISO 527
Yield strain	<b>11</b>	%	ISO 527
Strain at break	<b>550</b>	%	ISO 527
Shore D hardness	<b>69</b>	-	ISO 7619-1
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	<b>85</b>	°C	ISO 75-1/-2
Vicat softening temperature, A	<b>154</b>	°C	ISO 306
<b>Other properties</b>			
Density	<b>900</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Film Extrusion, Sheet Extrusion, Thermoforming

**Features**

High Gloss, Homopolymer

**Certifications**

Food contact

**Applications**

Packaging

**Regional Availability**

Asia Pacific