

HP561S

PP

Rayomand Petroleum and Energy Commercial Co.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	33	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1390	MPa	ISO 527
Yield stress	34	MPa	ISO 527
Yield strain	9.5	%	ISO 527
Strain at break	>50	%	ISO 527

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 0.45 MPa	81	°C	ISO 75-1/-2
Vicat softening temperature, A	153	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ISO 1183

Characteristics**Processing**

Fiber Extrusion, Other Extrusion

Regional Availability

Asia Pacific

Features

Gas Fading Resistance, Homopolymer