

**HY200**

PP

Hanwha TotalEnergies Petrochemical co. Ltd.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>2.4</b>	g/10min	ASTM D 1238

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>37.3</b>	MPa	ASTM D 638
Elongation at Break	<b>500</b>	%	ASTM D 638
Flexural Modulus	<b>1422</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 100</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>39.2</b>	J/m	ASTM D 256

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>910</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding, Other Extrusion

**Regional Availability**

Asia Pacific

**Features**

Homopolymer