

Indure X210A-UV NATRL

PP...

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	22	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	22	MPa	ISO 527
Flexural modulus, 23°C	1500	MPa	ISO 178

Other properties	Value	Unit	Test Standard
Density	970	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Delivery form

Natural Color

Features

Ductile, Scratch Resistant

Applications

Automotive

Regional Availability

North America