

Indure X225 NAV004 BLACK

PP...

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	40	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	26	MPa	ISO 527
Flexural modulus, 23°C	1300	MPa	ISO 178

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Features

Ductile, Scratch Resistant

Delivery form

Black

Applications

Automotive

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

North America