

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	6	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1500	MPa	ISO 527
Yield stress	34	MPa	ISO 527
Yield strain	9	%	ISO 527
Flexural modulus, 23°C	1500	MPa	ISO 178
Charpy notched impact strength, +23°C	4.5	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	48	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	96	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-2	class	IEC 60695-11-10
Thickness tested	1.6	mm	-

Other properties	Value	Unit	Test Standard
Density	920	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2	h	-
Processing humidity	≤0.07	%	-
Melt temperature	210 - 250	°C	-
Mold temperature	10 - 50	°C	-
Zone 1	190 - 240	°C	-

Characteristics

Processing

Injection Molding

Delivery form

Natural Color

Special Characteristics

Flame retardant

Features

Homopolymer

Applications

Electrical and Electronical

Regional Availability

Europe