

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	27	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	19.6	MPa	ISO 527
Flexural modulus, 23°C	966	MPa	ISO 178
Charpy notched impact strength, +23°C	49	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	48	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	77	°C	ISO 75-1/-2
Other properties			
Density	897	kg/m ³	ASTM D 792

Characteristics

Special Characteristics

High impact or impact modified

Features

Anti Slip

Applications

Automotive

Regional Availability

North America, South and Central America