

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	12	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	1.2	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Yield stress	35	MPa	ISO 527
Flexural modulus, 23°C	1400	MPa	ISO 178
Izod notched impact strength, +23°C	3.5	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Vicat softening temperature, B	85	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
Other properties			
Density	910	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Certifications

RoHS compliant

Special Characteristics

Anti-static, U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific, South and Central America