

**ISPLEN® NW080 M1**

PP

Repsol YPF S.A.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>800</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Other properties</b>			
Density	<b>905</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Blow Molding

**Features**

Homopolymer

**Regional Availability**

North America, Europe, South and Central America, Near East/Africa