

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	1.3	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Flexural modulus, 23°C	1200	MPa	ISO 178
Charpy notched impact strength, +23°C	60	kJ/m ²	ISO 179/1eA
Shore D hardness	60	-	ISO 7619-1
Thermal properties			
ISO Data			
Temp. of deflection under load, 0.45 MPa	83	°C	ISO 75-1/-2
Vicat softening temperature, A	150	°C	ISO 306
Other properties			
Density	905	kg/m ³	ISO 1183

Characteristics

Processing

Film Extrusion, Pipe/Tube Extrusion, Sheet Extrusion, Blow Molding

Special Characteristics

High impact or impact modified

Features

Copolymer

Certifications

Food contact

Regional Availability

North America, Europe, South and Central America, Near East/Africa