

ISPLEN® PB 170G1F

PP

Repsol YPF S.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	12	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Flexural modulus, 23°C	1200	MPa	ISO 178
Charpy notched impact strength, +23°C	8	kJ/m ²	ISO 179/1eA
Shore D hardness	62	-	ISO 7619-1
Thermal properties			
ISO Data			
Temp. of deflection under load, 0.45 MPa	85	°C	ISO 75-1/-2
Other properties			
Density	905	kg/m ³	ISO 1183

Characteristics**Processing**

Film Extrusion

Certifications

Food contact

Special Characteristics

High impact or impact modified

Applications

Packaging

Features

Low Gel, Copolymer

Regional Availability

North America, Europe, South and Central America, Near East/Africa