

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	5.6	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Yield stress	35	MPa	ISO 527
Flexural modulus, 23°C	1500	MPa	ISO 178
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	85	°C	ISO 75-1/-2
<b>Other properties</b>			
Density	905	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Processing

Other Extrusion

### Features

Homopolymer

### Certifications

Food contact

### Applications

Monofilament, Multifilament

### Regional Availability

North America, Europe, South and Central America, Near East/Africa