

ISPLEN® PR 264 M1F

PP

Repsol YPF S.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	9	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Flexural modulus, 23°C	950	MPa	ISO 178
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 0.45 MPa	70	°C	ISO 75-1/-2
Vicat softening temperature, A	138	°C	ISO 306
Other properties			
Density	905	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding, Film Extrusion, Other Extrusion

Certifications

Food contact

Additives

Antiblocking agent

Applications

Packaging

Special Characteristics

Transparent

Regional Availability

North America, Europe, South and Central America, Near East/Africa

Features

Blending Resin, Heat Sealable, Copolymer, Random Copolymer