

**ISPLEN® PR 264 S1F**

PP

Repsol YPF S.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	9	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Flexural modulus, 23°C	950	MPa	ISO 178
Charpy notched impact strength, +23°C	6	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	70	°C	ISO 75-1/-2
Vicat softening temperature, A	138	°C	ISO 306
<b>Other properties</b>			
Density	905	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding, Film Extrusion, Other Extrusion

**Certifications**

Food contact

**Additives**

Antiblocking agent

**Applications**

Packaging

**Special Characteristics**

Anti-static, Transparent

**Regional Availability**

North America, Europe, South and Central America, Near East/Africa

**Features**

Blending Resin, Heat Sealable, Copolymer, Random Copolymer