

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	35	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Flexural modulus, 23°C	1050	MPa	ISO 178
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 0.45 MPa	70	°C	ISO 75-1/-2
Other properties			
Density	905	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Additives

Release agent

Special Characteristics

Transparent

Features

High Crystallinity, Low Warpage, Copolymer, Random Copolymer

Certifications

Food contact

Applications

Electrical and Electronical, Packaging, Sports Equipment

Regional Availability

North America, Europe, South and Central America, Near East/Africa