

ITIPLEN IC M10 BK

PP

I.T.I. Poland Sp z o.o.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	10	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Flexural modulus, 23°C	1000	MPa	ISO 178
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	165	°C	ISO 11357-1/-3
Vicat softening temperature, B	60	°C	ISO 306
Other properties			
Density	930	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Features

Copolymer

Delivery form

Black

Regional Availability

Europe