

JET FLOW® ARPP200-2-JF Copolymer

PP

Aaron Industries Corp.

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|--------------|-------------|----------------------|
| ASTM Data | | | |
| Melt Flow Index, MFI | 60 | g/10min | ASTM D 1238 |
| Temperature | 230 | °C | - |
| Load | 2.16 | kg | - |
| Mold Shrinkage, MD | 0.022 | mm/mm | ASTM D 955 |

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Tensile Strength | 27.2 | MPa | ASTM D 638 |
| Flexural Modulus | 1110 | MPa | ASTM D 790 |
| Izod Impact notched, 1/8 in | 133 | J/m | ASTM D 256 |

| Thermal properties | Value | Unit | Test Standard |
|---------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| DTUL @ 66 psi | 108 | °C | ASTM D 648 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 910 | kg/m ³ | ASTM D 792 |

Characteristics**Features**

Copolymer

Certifications

Recycled Resin Content

Regional Availability

North America