

JM-380UN

PP

Lotte Chemical Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	60	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	25	MPa	ASTM D 638
Elongation at Break	10	%	ASTM D 638
Flexural Modulus	1270	MPa	ASTM D 790
Izod Impact notched, 1/8 in	59	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	29	J/m	ASTM D 256
Temperature	-10	°C	-

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	105	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Special Characteristics

U.V. stabilized or stable to weather

Features

Copolymer, Impact Copolymer

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific