

**JSS-350N**

PP

Lotte Chemical Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	10	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	29	MPa	ASTM D 638
Elongation at Break	100	%	ASTM D 638
Flexural Modulus	1765	MPa	ASTM D 790
Izod Impact notched, 1/8 in	98	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	19	J/m	ASTM D 256
Temperature	-10	°C	-

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 66 psi	135	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

High impact or impact modified, Heat stabilized or stable to heat

**Features**

Nucleated, Copolymer, Impact Copolymer

**Applications**

Automotive, General Purpose

**Regional Availability**

North America, Europe, Asia Pacific