

K7735

PP

SINOPEC Shanghai Gaoqiao Company

Processing/Physical Characteristics	Value	Unit	Test Standard
Other Standards^[5]			
Melt flow index, MFI	40	g/10min	

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
Other Standards^[5]			
Yield stress	24.5	MPa	
Flexural modulus, 23°C	1320	MPa	
Izod notched impact strength, +23°C	5	kJ/m ²	

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics

Features

Copolymer

Regional Availability

Asia Pacific