

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.7	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	3800	MPa	ISO 527
Stress at break	21	MPa	ISO 527
Strain at break	5.9	%	ISO 527
Charpy impact strength, +23°C	2.4	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	3.9	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	160	°C	ISO 11357-1/-3
Other properties			
ISO Data			
Density	2200	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
ISO Data			
Melt temperature	220 - 260	°C	-
Mold temperature	40 - 80	°C	-

Characteristics

Processing

Injection Molding

Regional Availability

Europe

Applications

Automotive, Electrical and Electronical