

Product Texts

JM-365 is high impact block copolymer which has high ethylene-propylene rubber content.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	26	g/10min	ISO 1133
ASTM Data			
Melt Flow Index, MFI	26	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	25	MPa	ISO 527
Strain at break	100	%	ISO 527
Flexural modulus, 23°C	1080	MPa	ISO 178
ASTM Data			
Tensile Strength at Yield	25	MPa	ASTM D 638
Elongation at Break	50	%	ASTM D 638
Flexural Modulus	1270	MPa	ASTM D 790
Izod Impact notched, 1/8 in	69	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	39	J/m	ASTM D 256
Temperature	-10	°C	-

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 0.45 MPa	85	°C	ISO 75-1/-2
ASTM Data			
DTUL @ 66 psi	105	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ISO 1183
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Special Characteristics

High impact or impact modified

Features

Copolymer, Impact Copolymer

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific