

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.6	%	ISO 294-4, 2577
ASTM Data			
Mold Shrinkage, MD	0.017	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	15	MPa	ISO 527
Flexural modulus	300	MPa	ISO 178
Flexural strength	10	MPa	ISO 178
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	40	kJ/m ²	ISO 179/1eA
Rockwell hardness	R 80	-	ISO 2039-2
ASTM Data			
Tensile Modulus	750	MPa	ASTM D 638
Tensile Strength	16	MPa	ASTM D 638
Flexural Modulus	640	MPa	ASTM D 790
Flexural Strength	18	MPa	ASTM D 790
Rockwell Hardness	R 80	-	ASTM D 785

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	163	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	75	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	135	°C	ISO 75-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
DTUL @ 66 psi	105	°C	ASTM D 648
DTUL @ 264 psi	60	°C	ASTM D 648
Melting Temperature	163	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Density	840	kg/m ³	ISO 1183
Density	860	kg/m ³	ASTM D 792

Characteristics

Special Characteristics
High impact or impact modified

Regional Availability
North America, Asia Pacific

Applications
Automotive