

# Kruplene PP Pellets black MFR 0,4-1,0

PP

Steinbeis PolyVert GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	0.7	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	1150	MPa	ISO 527
Charpy notched impact strength, +23°C	4.5	kJ/m <sup>2</sup>	ISO 179/1eA

Other properties	Value	Unit	Test Standard
Density	900	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Delivery form

Pellets, Black

### Features

Copolymer

### Certifications

Recycled Resin Content

### Regional Availability

Europe