

L-680

PP

Lotte Chemical Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	44	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	23	MPa	ASTM D 638
Elongation at Break	500	%	ASTM D 638
Flexural Modulus	685	MPa	ASTM D 790

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Vicat Temperature	120	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Coating

Regional Availability

North America, Europe, Asia Pacific

Features

Heat Sealable, Low Neck-In, Copolymer, Random Copolymer