

LATENE EP 7-V2HF

PP

LATI Industria Termoplastici S.p.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.5	%	ISO 294-4, 2577
Molding shrinkage, normal	1.5	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	1300	MPa	ISO 527
Yield stress	22	MPa	ISO 527
Yield strain	5.7	%	ISO 527
Stress at break	12	MPa	ISO 527
Strain at break	100	%	ISO 527
Charpy impact strength, +23°C	90	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	55	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	90	°C	ISO 75-1/-2
Vicat softening temperature, B	75	°C	ISO 306
Coeff. of linear therm. expansion, parallel	145	E-6/K	ISO 11359-1/-2
Glow Wire Flammability Index (GWFI)	850	°C	IEC 60695-2-12
GWFI - thickness tested (1)	1	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (2)	2	mm	-
Glow Wire Ignition Temperature (GWIT)	750	°C	IEC 60695-2-13
GWIT - thickness tested (1)	1	mm	-
Glow Wire Ignition Temperature (GWIT)	775	°C	IEC 60695-2-13
GWIT - thickness tested (2)	2	mm	-
ASTM Data			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	0.75	mm	-
Limiting Oxygen Index	26	%	ASTM D 2863
Electrical properties			
ISO Data			
Comparative tracking index	600	-	IEC 60112
ASTM Data			
Surface Resistivity	1E12	Ohm	ASTM D 257
Other properties			
Density	950	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	70 - 90	°C	-
Pre-drying - Time	3	h	-
Melt temperature	180 - 200	°C	-
Mold temperature	20 - 40	°C	-

Characteristics**Processing**

Injection Molding

Regional Availability

Europe

Features

Copolymer