

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.9	%	ISO 294-4, 2577
Molding shrinkage, normal	0.9	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	1000	MPa	ISO 527
Yield stress	10	MPa	ISO 527
Yield strain	1	%	ISO 527
Stress at break	8	MPa	ISO 527
Strain at break	2	%	ISO 527
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	5	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	60	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	95	°C	ISO 75-1/-2
Vicat softening temperature, B	95	°C	ISO 306
Electrical properties			
ASTM Data			
Surface Resistivity	1E12	Ohm	ASTM D 257
Other properties			
Density	780	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	70 - 90	°C	-
Pre-drying - Time	3	h	-
Melt temperature	180 - 200	°C	-
Mold temperature	40 - 60	°C	-

Characteristics

Processing

Injection Molding

Features

Copolymer

Regional Availability

Europe