

Lushan DP-1

PP

Guangzhou Lushan New Materials Co., Ltd

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------------|----------------------|
| ISO Data | | | |
| Flexural modulus, 23°C | 800 | MPa | ISO 178 |
| ASTM Data | | | |
| Tensile Strength | 25 | MPa | ASTM D 638 |
| Thermal properties | | | |
| ASTM Data | | | |
| Melting Temperature | 147 | °C | ASTM D 3418 |
| Other properties | | | |
| Moisture Content | 0.07 | % | - |
| Density | 895 | kg/m ³ | ASTM D 792 |

Characteristics**Processing**

Coating

Chemical Resistance

Oil Resistance

Delivery form

Powder

Regional Availability

Asia Pacific

Features

Good Adhesion