

Lushan PJ-1

PP

Guangzhou Lushan New Materials Co., Ltd

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	0.8	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	22	MPa	ASTM D 638
Elongation at Break	600	%	ASTM D 638
Thermal properties			
ASTM Data			
Vicat Temperature	145	°C	ASTM D 1525
Other properties			
Density	906	kg/m ³	ASTM D 792

Characteristics**Processing**

Other Extrusion, Coating

Features

Good Adhesion, Thermal Stability

Delivery form

Pellets, Granules, White

Regional Availability

Asia Pacific

Special Characteristics

U.V. stabilized or stable to weather