

Lushan PR296B

PP

Guangzhou Lushan New Materials Co., Ltd

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	5	g/10min	ASTM D 1238
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Elongation at Break	300	%	ASTM D 638

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	155	°C	ASTM D 3418
Vicat Temperature	100	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Other Extrusion

Regional Availability

Asia Pacific

Features

Good Adhesion