

Lushan RF1000

PP

Guangzhou Lushan New Materials Co., Ltd

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	2.5	g/10min	ASTM D 1238
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Elongation at Break	680	%	ASTM D 638

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	126	°C	ASTM D 3418
Vicat Temperature	92	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	926	kg/m ³	ASTM D 792

Characteristics**Features**

Good Adhesion, Weldable

Regional Availability

Asia Pacific