

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	3.9	cm <sup>3</sup> /10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	1350	MPa	ISO 527
Yield stress	25	MPa	ISO 527
Yield strain	6	%	ISO 527
Charpy notched impact strength, +23°C	15	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Other properties</b>			
Density	905	kg/m <sup>3</sup>	ISO 1183
<b>Processing Recommendation Injection Molding</b>			
Melt temperature	<260	°C	-
Mold temperature	10 - 30	°C	-
Zone 1	210 - 230	°C	-
Zone 2	220 - 240	°C	-
Zone 3	230 - 250	°C	-
Nozzle temperature	240 - 260	°C	-

## Characteristics

### Processing

Injection Molding

### Delivery form

Pellets

### Special Characteristics

High impact or impact modified

### Certifications

Contains renewable resources

### Regional Availability

Europe