

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	15	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Flexural modulus, 23°C	1100	MPa	ISO 178
Charpy notched impact strength, +23°C	7	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	6	kJ/m ²	ISO 180/1A
Other properties			
Density	910	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	60 - 80	°C	-
Pre-drying - Time	2 - 4	h	-
Mold temperature	30 - 60	°C	-
Zone 1	210 - 260	°C	-

Characteristics

Processing

Injection Molding

Delivery form

Natural Color

Features

Copolymer

Certifications

Recycled Resin Content

Regional Availability

Europe