

Matrixx 12N4002

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	8	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mold Shrinkage, MD	0.019	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	31	MPa	ASTM D 638
Flexural Modulus	1310	MPa	ASTM D 790
Gardner Impact	16.9	J	ASTM D 2794,4226,5420
Izod Impact notched, 1/8 in	80	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 66 psi	90.6	°C	ASTM D 648
Other properties			
Density	938	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Pellets

Features

Non Blooming

Special Characteristics

Flame retardant

Regional Availability

North America