

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	34	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Modulus	1170	MPa	ASTM D 638
Tensile Strength at Yield	26.2	MPa	ASTM D 638
Izod Impact notched, 1/8 in	27	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	68.3	°C	ASTM D 648
Processing Recommendation Injection Molding			
Mold temperature	16 - 50	°C	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Applications

Building Construction, General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa