

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength at Break	<b>13.8</b>	MPa	ASTM D 412
Elongation at Break	<b>320</b>	%	ASTM D 412
<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Limiting Oxygen Index	<b>31</b>	%	ASTM D 2863
<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Dielectric Constant, 1 MHz	<b>3.06</b>	-	ASTM D 150
<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1500</b>	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Wire/Cable Extrusion, Other Extrusion

#### Special Characteristics

Flame retardant, Halogen-free

#### Delivery form

Pellets

#### Regional Availability

North America