

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Tensile Strength at Break | 15.9 | MPa | ASTM D 412 |
| Elongation at Break | 320 | % | ASTM D 412 |

| Thermal properties | Value | Unit | Test Standard |
|---------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| UL 94 Flame rating | V-0 | - | UL 94 |
| Thickness tested | 1.6 | mm | - |
| Limiting Oxygen Index | 34 | % | ASTM D 2863 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 1460 | kg/m ³ | ASTM D 792 |

Characteristics

Processing
Wire/Cable Extrusion, Other Extrusion

Special Characteristics
Flame retardant

Delivery form
Pellets

Regional Availability
North America