

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	15.9	MPa	ASTM D 412
Elongation at Break	320	%	ASTM D 412

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Limiting Oxygen Index	34	%	ASTM D 2863

Other properties	Value	Unit	Test Standard
Density	1460	kg/m ³	ASTM D 792

Characteristics

Processing

Wire/Cable Extrusion, Other Extrusion

Special Characteristics

Flame retardant

Delivery form

Pellets

Regional Availability

North America