

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	3.6	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	23.4	MPa	ASTM D 638
Elongation at Break	400	%	ASTM D 638
Other properties			
Density	450	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding, Wire/Cable Extrusion, Other Extrusion

Delivery form

Pellets

Features

Foamable, Copolymer

Applications

Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa