

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	20	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	39	MPa	ASTM D 638
Elongation at Yield	8	%	ASTM D 638
Rockwell Hardness	R 110	-	ASTM D 785
Gardner Impact	3	J	ASTM D 2794,4226,5420
Izod Impact notched, 1/8 in	30	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
DTUL @ 66 psi	108	°C	ASTM D 648
Melting Temperature	162	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	226 - 246	°C	-
Mold temperature	15 - 49	°C	-

Characteristics

Processing

Injection Molding

Special Characteristics

Transparent

Features

Nucleated, Homopolymer

Certifications

Food contact, Food approval FDA 21 CFR, Medical Grade, Biocompatibility ISO 10993, US Pharmacopeia Class VI Approved, Drug Master File, RoHS compliant

Applications

Medical

Regional Availability

North America