

Metocene MF650Y

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	2500	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Melt flow index, MFI	1800	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
ASTM Data			
Melt Flow Index, MFI	1800	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Other properties			
Density	910	kg/m ³	ASTM D 792

Characteristics**Processing**

Film Extrusion

Delivery form

Granules

Features

Low Smoke, Thermal Stability, Homopolymer

Certifications

Food contact, Food approval 1935/2004/EC, Food approval 10/2011, Food approval FDA 21 CFR

Regional Availability

North America, Near East/Africa