

**Moplen 2000HEXP**

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	<b>16</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	<b>1000</b>	MPa	ISO 527
Yield stress	<b>19</b>	MPa	ISO 527
Yield strain	<b>5</b>	%	ISO 527
Stress at break	<b>14</b>	MPa	ISO 527
Strain at break	<b>100</b>	%	ISO 527
Charpy notched impact strength, +23°C	<b>17</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>163</b>	°C	ISO 11357-1/-3
Temp. of deflection under load, 0.45 MPa	<b>84</b>	°C	ISO 75-1/-2
Vicat softening temperature, A	<b>140</b>	°C	ISO 306
<b>Other properties</b>			
Density	<b>890</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets, Natural Color

**Special Characteristics**

High impact or impact modified

**Features**

Copolymer, Impact Copolymer

**Applications**

Automotive, Packaging

**Regional Availability**

Europe, Near East/Africa