

**Moplen EP336J**

PP

PolyMirae

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	3	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	24.5	MPa	ASTM D 638
Elongation at Yield	7	%	ASTM D 638
Flexural Modulus	1177	MPa	ASTM D 790
Rockwell Hardness	R 86	-	ASTM D 785
Izod Impact notched, 1/8 in	425	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	56.7	J/m	ASTM D 256
Temperature	-20	°C	-
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	96	°C	ASTM D 648
Vicat Temperature	147	°C	ASTM D 1525
<b>Other properties</b>			
Density	900	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

High impact or impact modified

**Features**

Low Warpage, Copolymer

**Certifications**

Food contact, Food approval FDA 21 CFR

**Regional Availability**

Asia Pacific, Near East/Africa